

SHANDONG SANYI GROUP CO., LTD

NO.135 HUILONGSHAN RD. LONGSHAN HIGH-TECH INDUSTRIAL PARK.
LINOU, WEIFANG, SHANDONG

CERTIFICATE OF ANALYSIS

CONTRACT NO.: SYLGH230525

DATE _____

2023-08-07 LC ND

1185FLC200011 DATE: 230608

CHLORINATED POLYETHYLENE

CPE 139A

Book No. : 23061305

Analysis Items	Specification	Results
Chlorine content (%)	33±1	35.7
Heat of fusion (J/g)	≤2.0	0.55
Screen tailings(0.9mm aperture) (%)	≤2.0	0.30
Tensile strength(Mpa)	≥6.0	11.0
Shore A hardness (Shore A)	≤85	56
Impurity particle PC/50g	≤10	2
Elongation at break (%)	≥650	675
CaCO3 content (%)	≤5	4.0

THE GOODS ARE FREELY IMPORTABLE UNDER CHAPTER 2 OF FOREIGN TRADE POLICY 2014-2024

ISSUED BY BENEFICIARY

SHANDONG SANYI GROUP
CO.,LTD